

Description

The 400-NS series *No-Clean Super Wick* are high quality, precision cleaned desoldering braids that were produced with up-to-date and environmentally friendly processes and technology. The high purity copper conducts heat fast, allowing for faster wicking and shorter dwell time that minimizes possible overheating damages.

Benefits and Features

- **Conforms to MIL-F-14256E RMA flux and J-STD-004**
- **High purity, oxide-free copper**
- **ESD (Electrostatic Dissipative) safe for 1.5 m [5 ft] bobbins**
- **Environmentally and PCB safe residues**
- **Suitable for Use in Food Facilities as a Non-Food Chemical**—Canadian and NFS recognition letters available on request

ENVIRONMENT

- ✓ RoHS
- ✓ REACH compliant

Desoldering Braid Selection Guide

Cat No.	Width		Length		ESD Safe Spools	Label Color Code
	in	mm	ft	m	anti-static	
424-NS	0.06	1.5	5	1.5	Yes	YELLOW YELLOW
424-NS-10 ^{a)}	0.06	1.5	5	1.5	Yes	
425-NS	0.08	2.0	5	1.5	Yes	GREEN GREEN GREEN
425-NS-10 ^{a)}	0.08	2.0	5	1.5	Yes	
453-NS	0.08	2.0	49	15.0	No	
426-NS	0.10	2.5	5	1.5	Yes	BLUE BLUE
454-NS	0.10	2.5	49	15.0	No	

a) Packs of 10

Flux Properties

High temperature, mildly activated rosin flux.

Physical Properties	Method	Value
Flux Classification	Conforms to MIL-F-14256F J-STD-004	R (Rosin) ROL0
Flux Percentage	—	<5%
Corrosion	JIS Z 3197 and QQ-SS-571d	Non-corrosive residue
Cleaning Requirements	—	Not required

Compatibility

Chemical—the flux residue from the Super Wick is inert under normal conditions. The flux residue can be cleaned with a flux cleaner like the MG 4140 or 413B.

Storage

Keep away from moisture. Shrink wrapping is recommended for extended storage. Store between 22 and 27 °C [72 and 81 °F] in dry area away from sunlight.

Health, Safety, and Environmental Awareness

Please see the 400-NS Series **Safety Data Sheet** (SDS) for more details on transportation, storage, handling and other security guidelines.

Braid Desoldering Instructions

Wicking works best for the removal of surface solders. This desoldering method is generally not recommended for removal of solder in through plated holes. While the use of desoldering (wicking) braids is not hard, it does require a moderate to advance skill level depending on the project. Novices should practice on scrap pieces before attempting to an actual repair.

Equipment and Material Needed

- Solder iron equipped with a chisel tip that matches the size of the wick
- Damp sponge
- Scissors
- (Optional) flux—like the *MG 8341 No Clean Flux Paste*
- (Optional) cleaners—like the *MG 4140 Flux Remover* or *413B Heavy Duty Flux Removers*

Preparation Steps

- Remove conformal coating that may be present.
- Clean residues/oxides that are present using a flux remover.
- For lead-free solder, start with tip temperature of about 315 °C and adjust as necessary.
- Choose a braid that matches the size of the solder to be removed. If there are small beads, choosing a wider braid will also speed up the desoldering process.

To Remove Surface Solder

1. Heat up the soldering iron.
2. (Optional) Apply flux to the lead or land area.
3. Set the braid on the solder to be removed.
4. Place the solder tip on the braid, avoiding contact with other components.
5. When wicking action has ceased, remove the soldering iron and braid together in perpendicular motion from the surface.
6. Let the area cool, clean the tip with the sponge, and repeat removal steps as necessary.
7. Clean flux residue that may have accumulated.

ATTENTION: Do NOT let braid solidify on the joint.

TIP! To avoid “drag whiskers”, do not move the wick along the surface during desoldering.

TIP! Be careful not to overheat

TRICKS: When the solder bead to be removed is very thin, adding a little bit of solder to the joint prior to the removal attempt can help.

TRICKS: Cutting an oversized braid at an angle with scissors can help with desoldering small areas.



ISO 9001 Registered Quality System.
Burlington, Ontario, Canada QMI File # 004008

No-Clean Super Wick 400-NS Series Technical Data Sheet

400-NS Series

To Put Away the Soldering Iron

- Re-tin tip with solder and place the soldering iron on its stand.

Supporting Products

Flux Cleaners

- *Flux Remover for PC Boards*: Cat. No. 4140-P, 4140-1L, 4140-4L, 4140-20L
- *Heavy Duty Flux Remover*: Cat. No. 413B-1L, 413B-4L, 413B-20L

Thinners & Conformal Coating Removers

- *Thinner 2*: Cat. No. 4352-945ML, 4352-4L (1 gal), 4352-20L, 4352-200L
- *Conformal Coating Stripper*: Cat. No. 8310-100ML

Tip Tinner

- *Tip Tinner*: Cat. No. 4190-28G

Electronic Cleaners

- *Safety Wash Electronics Cleaner*: Cat. No. 4050A-340G, 4050-1L, 4050-4L, 4050-20L
- *Superwash Cleaner Degreaser*: Cat. No. 406B-450G
- *Isopropyl Alcohol*: Cat. No. 824

Technical Support

Contact us regarding any questions, improvement suggestions, or problems with this product. Application notes, instructions, and FAQs are located at www.mgchemicals.com.

Email: support@mgchemicals.com

Phone: +(1) 800-340-0772 (Canada, Mexico & USA)
+(1) 905-331-1396 (International)

Fax: +(1) 905-331-2862 or +(1) 800-340-0773

Mailing address: **Manufacturing & Support**
1210 Corporate Drive
Burlington, Ontario, Canada
L7L 5R6

Head Office
9347-193rd Street
Surrey, British Columbia, Canada
V4N 4E7

Disclaimer

This information is believed to be accurate. It is intended for professional end users having the skills to evaluate and use the data properly. *M.G. Chemicals Ltd.* does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.